

96 & 908 NP Metallic Silvers

Available Phthalate Compliant or Non-Phthalate (NP)

INTERNATIONAL COATINGS CO., INC.

13929 East 166th Street • Cerritos, California, USA 90702-7666 • Voice (562) 926-1010 • Fax (562) 926-9486 • www.iccink.com

GENERAL INFORMATION

96* and 908* Metallic Silvers are plastisol based products that produce a "chrome" metallic look when printed. 96LF and 908 produce the best look when directly printed onto a garment or fabric.

*Lead Compliant (Contains less than 90 ppm lead)

RECOMMENDED FABRICS

96LF is recommended for use on cotton and some cotton/polyester blends. 908 is recommended for shell nylon and other nylon materials. 96 and 908 are not low bleed products. **Pre-print and test all printed fabrics for possible dye migration and wash durability before beginning production.**

INK APPLICATION

96 Metallic Silver comes ready for use and should be printed without modification. Stir ink well prior to each use. For best visual results, this ink should be printed last in a design.

908 Metallic Silver must be mixed with 900 Catalyst to ensure best adhesion to nylon fabrics. 900 Catalyst is available in 2 oz. and 8 oz. containers. It should be hand stirred into the ink thoroughly to the following proportions:

By Volume: 16 parts Ink to 1 part 900 Catalyst.

By Weight: 20 parts Ink to 1 part 900 Catalyst.

Ink may be used immediately after mixing. Do not mix more ink and catalyst than is needed for a job. Pot life of mixed ink is 4 to 8 hours. Over catalyzation will shorten pot life of ink.

SCREEN MESH AND EMULSION

86-125 t/in or 34-49 t/cm Monofilament Mesh.

Any direct, indirect or capillary lacquer resistant emulsion.

SQUEEGEE

65-75 Durometer: Sharp or Beveled Edge

60-90-60 Triple Durometer: Sharp Edge

DRYER TEMPERATURES

325°F (163°C) Fusion temperature for entire ink film.

Plastisols do not air dry. They must be fused with an appropriate heat source to assure maximum durability. The optimum time/temperature cycle will vary with the amount of ink deposited, fabric and the type of heat source used. Plastisols achieve the proper fusion point as soon as the innermost section of the ink film reaches the prescribed temperature. Test dryer temperatures before beginning a production run. Wash test printed product before production run.

IMPORTANT INFORMATION

Caution: 96 and 908 Metallic Silver both contain a high loading of un-coated metallic powders that will tarnish (turn gray) when exposed to any type of detergent or water that contains a bleaching or whitening agent. The abrasion resistance of these inks is also low. There will be some rub off of metallic particles even when the inks are properly cured/fused. It is extremely important to pre-print and test printed fabrics for wash and wear durability before beginning production.

1. 96 and 908 Metallic Silver reflect infrared heat. A forced air dryer is highly recommended for proper curing/fusion of these products. Complete fusion of these products may be very difficult to achieve in an infrared dryer. Even when the 96 and 908 are properly fused, there will be some rub off of metallic particles. Check for proper cure/fusion of product by wash testing finished product according to the wash instructions below.
2. To obtain best wash results, make sure printed inks are properly cured/fused and hand wash with a phosphate free detergent such as Woolite[®], then air or line dry. Do not use bleach, iron or dry clean the printed garment.
3. Air drying washed product is strongly recommended. Dulling of ink surface may be caused by heat and abrasion in a clothes dryer.
4. Garments printed with 96 or 908 should be labeled with recommended washing instructions.
5. Use 156 Metallic Silver Shimmers when best overall wash and wear durability is desired for metallic looking prints.

PRODUCT INFORMATION

STORAGE OF INK CONTAINERS

Keep containers well sealed when not in use. Keep indoors and store in a cool area. Recommend storage at 65°F to 90°F (18°C TO 32°C). Avoid storage in direct sunlight or in extreme temperature conditions.

CLEAN-UP

Any environmentally friendly plastisol screen wash or mineral spirits.

PRODUCT PACKAGING

Quart, 1 Gallon, 5 Gallon, or 30 Gallon Containers

PRODUCT MSDS

Refer to Material Safety Data Sheet MSDS8